



YOUNG'S CORPORATION

242-8 YANGJAE-DONG, SEOCHO-GU, SEOUL, 137-132, KOREA
TEL: 82-2-555-1040 FAX: 82-2-2057-0399
E-mail: export@youngscorp.com Website: www.youngscorp.com

NMA (n-methylol acrylamide 48%)

- Crosslinking Agent in Polymerization

- Major Properties

- : Improved water and solvent resistance
- : Improved adhesion
- : Improved textile strength
- : Flexibility
- : Improved impact resistance

Item	Analysis Result
Color, APHA	40
Molecular Weight	101
Acrylamide, % by Weight	5.0 Max
Total Solids, % by Weight by Bromination	48.0
Free Formaldehyde, % by Weight	2 Max
pH(as is)	7.53
Specific Gravity at 25 °C (77°F)	1.08
Crystallization Point	-10 °C (14°F)
Homopolymer Tg	34 °C